

APCODUR HB EPOXY ZINC PHOSPHATE PRIMER-QD

Anti-corrosive Epoxy Primer



PRODUCT DESCRIPTION

Two component, high build quick drying epoxy primer with zinc phosphate pigment

Features and Recommended Use

- Designed as an epoxy primer or build coat in protective coating systems
- Excellent resistance to saline, marine, and chemical environments
- Free from lead and chromate containing pigment
- Suitable for carbon steel

Technical Data

Colour	Grey / Red Oxide
Gloss	Matt
Volume Solids	Approx. 60%
Recommended DFT (Dry Film Thickness) per Coat	80–120 microns
Theoretical Covering Capacity	8 sq. mtr/ltr @ 80 microns DFT; 5 sq. mtr/ltr @ 120 microns DFT
Drying Time at 30°C – Surface Dry	10 minutes
Tack free	30 minutes
Drying Time at 30°C – Hard Dry	3 hours
Drying Time at 30°C – Full Cure	7 days
Overcoating Interval at 30°C – Minimum	4 hours
Overcoating Interval at 30°C – Maximum	1 month (surface must be dry and clean from all contamination)

The data given is for guideline only. The physical values are subject to normal manufacturing tolerances, colour and testing variances. The volume solids indicated are as per ASTM D 2697 air drying method. The actual drying time/overcoat interval may be shorter or longer, depending on film thickness, ventilation, humidity, temperature etc. The information provided above is at 30°C and 65% relative humidity.

DIRECTION FOR USE

Surface Preparation

MIXING

- Apcodur HB Epoxy Zinc Phosphate Primer-QD, is supplied in two packs. Stir the base and hardener separately. If settling is observed in the base or hardener, loosen the settled material with the help of hand stirrer followed by power driven stirrer (at lower RPM) for quick homogenous mixing.
- Mix hardener gradually into the base under continuous stirring as per the mixing ratio. Once the unit has been mixed, it should be consumed within the working pot life. In case of part mixing (which should be avoided), close the lids of containers tightly to avoid contact with atmospheric moisture.
- Thinner should be added after mixing the components and post the induction time. Addition of excessive thinner will lead to reduced sag resistance.

Mixing Ratio : Base: Hardener
 (By volume) : 4 : 1
 Induction Time : 30minutes
 Pot life at 30°C : 5 hours

APPLICATION

Air Spray:

Recommended thinner : Apcodur Epoxy Thinner/Thinner T 141
 Volume of thinner : 10 - 20%
 Nozzle orifice : 1.5 – 3.0 mm
 Nozzle Pressure : 0.3 – 0.4 MPa (= approx. 3 – 4 atm; 43 – 47 p.s.i.)
 Cleaning Thinner : Apcodur Epoxy Thinner/Thinner T 141

Airless Spray:

Recommended thinner : Apcodur Epoxy Thinner/Thinner T 141
 Volume of thinner : 0 - 15%
 Nozzle orifice : 0.33 - 0.41 mm (13 – 16 Thou)
 Nozzle Pressure : 16-20 MPa (= approx. 160-200 atm; 2300-2800 p.s.i.)
 Cleaning Thinner : Apcodur Epoxy Thinner/Thinner T 141

Brush / Roller

Suitable for stripe coating and small areas.
 Recommended thinner : Apcodur Epoxy Thinner/Thinner T 141
 Volume of thinner : 5 - 15%

CLEANING

- ⌋ Do not allow the product to remain in hoses, gun or spray equipment. Clean all equipment immediately after use with Epoxy Thinner/Thinner T 141. It is recommended to periodically flush out spray equipment during the course of the working day. The frequency of cleaning will depend on amount sprayed, temperature and time gap.
- ⌋ All surplus material and empty containers should be disposed of in accordance with appropriate regional legislation.

PRODUCT CHARACTERISTICS

- ⌋ Higher film build up in single coat can be attained only by airless spray. Conventional air spray or application using pressure pot may require multiple coats to achieve desired film build. Restrict brush and roller application only for stripe coat and for smaller areas.
- ⌋ The maximum performance is achieved after complete curing.
- ⌋ As common with all epoxies Apcodur HB Epoxy Zinc Phosphate Primer-QD will chalk and discolor on exterior exposure. However, these phenomena are not detrimental to anti-corrosive performance. The actual rate of chalking will depend upon climatic conditions and will normally be limited to a thin surface layer.

General

- ┆ Surfaces must be dry, clean and free from contaminants
- ┆ Ensure removal of dirt, dust, oil and all other contaminants that could interfere with adhesion of the primer. Oil and grease should be removed as per SSPC-SP1solvent cleaning with aromatic solvents.
- ┆ Surface should be checked and treated in accordance with ISO 8504 prior to priming

Blast Cleaning

- ┆ Steel, abrasive blast clean to min. Sa 2 ¹/₂ (ISO 8501-1: 200) or SSPC-SP 10. In case oxidation has occurred between blasting and application of Apcodur HB Epoxy Zinc Phosphate Primer-DQ, the surface should be re-blasted.
- ┆ A blasting profile of (Rz) 30 - 50 microns is recommended.
- ┆ Substrate temperature should be at least 3°C above dew point but not above 50°C.
- ┆ Relative humidity should be below 85%
- ┆ Good ventilation is required in confined areas to ensure proper curing

PACK SIZE	5ltr (Base : 1 × 4 ltrs & Hardener : 1 × 1 ltrs) 20ltr (Base : 1 × 16 ltrs & Hardener : 1 × 4 ltrs)
STORAGE	Shelf Life: Atleast 12 months @ 30°C for original unopened pack, subject to inspection thereafter. Store in a cool, dry place and in accordance with local regulations. Store in a cool, dry place and in accordance with local regulations
REGULATORY INFORMATION	Flash Point Base : Not less than 24°C Hardener : Not less than 24°C
	VOC 100 gm/ ltr as per USA-EPA Method 24

SAFETY INFORMATION

As a general safety measure, inhalation of solvent vapours or coating mist and contact of coating with skin & eyes should be avoided. Forced ventilation should be provided when applying coating in confined spaces or stagnant air. Even when ventilation is provided, respiratory, skin and eye protection are always recommended when spraying the coating. Please refer our Material Safety Data Sheet prior to using the product.

Disclaimer:

To the best of our knowledge the information provided herein are true and accurate at the date of issuance. Since we have no control over the quality or condition of the substrate or the various factors affecting the use and application of the product, we do not accept any responsibility or liability arising out of use of the product. The company reserves the right to modify data contained herein without prior notice. Any change in data would normally be followed by issue of a new data-sheet. The user should check with the nearest sales office of the company and confirm the validity of the information, prior to using the product.