asianpaints

PRODUCT CODE 0032

Decora Cement Paint

Asian Paints Decora Cement Paint coating is a specially treated cement- based economy exterior/interior wall finish suitable for usage in dry conditions.

WATER BASED

LEAD FREE*GUARANTEE

* All Asian Paints products contain no added Lead, Mercury, Arsenic or Chromium from April 2008.

PRODUCT BENEFITS

1. Its give good hardness
2. Can be applied both interior & exterior surface.
3. Does not chalk and can be applied on adequately cured fresh plaster
4. Economy & durable in varying weather conditions.

PRODUCT FEATURES

AVAILABLE PACKS

COLOURS AVAILABLE

White*

26*



COVERAGE

On smooth masonary surface by brushing

1 COAT

90 - 110 sq.ft/ltr**

**Actual coverage may vary from the quoted coverage due to factors such as method and condition of application and surface roughness and porosity.

DRYING TIME TO RECOAT



4-5 HOURS

RECOMMENDED USAGE

It can be used on all types of exterior/interior cement plasters, exterior ceilings, asbestos sheets, concrete urfaces.

HOW TO APPLY

PRE PAINTING STEPS

PLASTER New masonary surfaces must be allowed to cure completely. It is recommended to allow 28 days as the curing time for new masonary surfaces.

CLEANING Ensure that surface is completely free from all dirt, loosely held plaster, powdery residue, oil, grease or any other contamination. Any previous growth of fungus, algae or moss needs to be removed thoroughly by vigorous wire brushing and cleaning with water.

FILLING FOR HOLES & DENTS
In case of dents and holes use Asian Paints TruCare Wall Putty or white cement and fine sand in the ratio 1:3.

APPLICATION PROCESS

APPLICATION	CODE	THINNER	DILUTION %	APPLICATION VISCOSITY[1]	RECOATING PERIOD
STEP 1 SANDING	SAND THE SURFACE WITH EMERY PAPER 180 AND WIPE CLEAN				
STEP 2 SURFACE WETING	SATURATE THE SURFACE WITH CLEAN WATER AND ALLOW TO DRY PARTIALLY BEFORE APPLICATION				
STEP 3 ASIAN PAINTS DECORA CEMENT PAINT BRUSH	0032	WATER	80-100%	BRUSH	4 - 5 HRS
STEP 4 ASIAN PAINTS DECORA CEMENT PAINT BRUSH	0032	WATER	80-100%	BRUSH	4 - 5 HRS

1 .Recoat period is quoted for 25°C and 50% Relative Humidity, these may vary under different conditions.

ADDITIONAL INFORMATION

POST PAINTING CARE

Cure the surface with water 2-3 times

TECHNICAL DETAILS

a. Drying time: Surface dry time 30 min

b.

c. Stability of thinned paint: To be used within 2.5 hours

PRECAUTIONS

- Do not apply when ambient temperature is less than 10°C or if the temperature might drop to this level within 4 hrs of application.
- Do not over-thin or over-extend the brush
- Do not use Apcolite Universal Stainers or any other colourants
- Stir well and strain before use
- In coastal areas, it is not recommended to leave the primer without the application of top coats for a long period of time

SAFETY FEATURES

- Kindly refer to the MSDS for Asian Paints Decora Cement Paints which gives detailed information on safety measures while handling the paint.
- Store the container with the lid tightly closed in an upright position, in a cool, dry place
- Keep out of reach of children and away from food, drink
- May be harmful if swallowed. In case of ingestion seek immediate medical attention.
- Wear eye protection during application. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
- In case of skin contact immediately wash skin with soap and plenty of water. Get medical attention if irritation develops or persists.
- Do not breathe vapour or spray.It is recommended to wear suitable nose pad during sanding and surface preparation to avoid dust inhalation
- Do not pour leftover paint down the drain or in water courses.
- In the event of spills, contain spillage using sand or earth.
- Safety Data Sheet available on request.
- No added Lead, Mercury or Chromium compounds

WeAssure Helpline

For enquiries, feedback and complaints, please call toll-free number **09612003355** or write to us at **weassure.apbl@asianpaints.com**

Version No. VN01/01/2022

Asian Paints Bangladesh Ltd.
Head Office: The Pearl Trade Centre (PTC), Cha-90/3, Progoti Sarani, North Badda, Dhaka - 1212. Phone: 09612003355
Factory & Registered Office: Gazipur Factory: Plot# 317 & 757, Bahadurpur, Gazipur-1703 | Mirsarai Factory: Plot # 36, Zone 6, Mirsarai Economic Zone, Chittagong - 4324