

PRODUCT CODE BD1 - F0082

## Timber Glaze

Asian Paint Timber Glaze Decorative Pigmented Varnish is a Polyurethane modified clear coating, which offers multiple shades to enhance the beauty of wooden doors, windows and furniture within affordable budget.

### PRODUCT BENEFITS

**Highest Gloss**

Best Gloss in the category

**Popular Shade Availability**

Multiple shades to choose from based on preference

**Easiest Application**

Ready-to-use, quick application by using a brush or by spraying

**Water Resistance**

Prevents water penetration



OIL BASED

**LEAD FREE GUARANTEE**

\* All Asian Paints products contain no added Lead, Mercury, Arsenic or Chromium from April 2008.

### PRODUCT FEATURES

#### DURABILITY




✓ MODERATE

#### COLOURS AVAILABLE

**Range of 6 attractive shades available.**

Clear, Teak, Golden Pine, Rust, Mahogany, Rosewood\*



#### COVERAGE


On normal masonry surface after brushing



**2-3 COATS**  
(25-30 sq.mtr/ltr / coat)

\*\*Actual coverage may vary from the quoted coverage due to factors such as method and condition of application and surface roughness.

#### AVAILABLE PACKS



0.91 ltr

#### FINISH



GLOSS SILK MATT HIGH SHEEN HIGH GLOSS

✓ GLOSSY

Refer to sheen levels in technical details

### HOW TO APPLY

#### PRE PAINTING STEPS



**CLEANING** Using sand paper no. 120. Wipe surface to clean off loose dust particles, oily substance.



**DENT FILLING** If the surface has dents, apply Filler with a putty knife over the dented area.

**RAGGING** Apply Woodtech For Interior & Exterior by Ragging. Allow to dry for 30-120 minutes.

#### PAINT APPLICATION PROCESS

APPLICATION	CODE	THINNER	APPLICATION VISCOSITY <sup>1</sup>	RECOATING PERIOD
STEP 1 TIMBER GLAZE 1st COAT BRUSH/ROLLER/SPRAY	BD1-F0082	THINNER T101	SPRAY 20 - 25 secs BRUSH 30 - 40 secs	8 - 10 hours
STEP 2 SANDING	SAND THE SURFACE WITH SAND PAPER 320 OR 400 AND WIPE CLEAN			
STEP 3 TIMBER GLAZE 2nd COAT BRUSH/ROLLER/SPRAY	BD1-F0082	THINNER T101	SPRAY 20 - 25 secs BRUSH 30 - 40 secs	8 - 10 hours

Note:

1. If required, apply Asian Paints Timber Glaze by brushing on sanded wooden surface and allow 4-6 hours of drying time.
2. Do not store Asian Paints Timber Glaze in a half filled container to avoid skin formation. Transfer container to a smaller container so as to leave no air gap.
3. Take care to cap the container tightly after use.
4. Asian Paints Timber Glaze must not be polluted with oil, varnish or the like and must not be sanded with steel wool between coats.
5. Recoat period is quoted for 30°C and 75 relative humidity, these may vary under different conditions.
6. Spraying air pressure 2.2 to 2.8 kgs.sq.cm.
7. Viscosity as measured through a Ford cup B4 at 30°C.

## ADDITIONAL INFORMATION

### POST PAINTING CARE

For best performance ensure dry dust cleaning at regular intervals. Allow drying time of 3 weeks for proper film formation before any sponge cleaning with mild soap solution.

### PRECAUTIONS

- > For optimum performance, Asian Paints Timber Glaze must be applied at a temperature between 20°C and 40°C and humidity not above 75%
- > Do not over-thin and mix according

### TECHNICAL DETAILS

- a. Drying time:** Surface dry time 60 minutes. Tack Free time 4 hrs.
- b. Flash point:** (IS 101/1987, Part 1, Sec 6): Above 30°C (86°F)
- c. Stability of thinned paint:** To be used within 24 hours
- d. Shelf Life:** 3 years from date of manufacture in original tightly closed container away from direct sun light and extensive heat.

### SAFETY FEATURES

- > Store the product at ambient conditions in well ventilated locations and away from source of ignition and fire
- > Use protective equipment like rubber/polyurathene gloves, safety goggles/glasses, face mask while handling the paint
- > Avoid eye and skin contact. In both cases wash with soap and plenty of water. Get medical attention if irritation develops or persists.
- > Do not inhale or ingest. In case of inhalation move to fresh air and seek medical attention if symptoms persist in both cases
- > Do not dispose in any drain or land filling. No added Lead, Mercury or Chromium compounds
- > Flammable



For enquiries, feedback and complaints, please call toll-free number **09612003355** or write to us at **weassure.apbl@asianpaints.com**