

## Breemo Alkyd Topcoat Fast Dry

Fast drying Alkyd topcoat

### DESCRIPTION & USES

- **Breemo Alkyd Topcoat Fast Dry** is a modified alkyd based topcoat formulated to apply on steel and wood after suitable priming. Suitable for protection of structural steel in moderate corrosive environments.
- Fast dry properties help to improve the shop floor productivity.
- For Exterior and Interior use depending on color.

### PROPERTIES

|                                               |                                                                                                               |
|-----------------------------------------------|---------------------------------------------------------------------------------------------------------------|
| Finish                                        | Smooth/ Semigloss/Glossy                                                                                      |
| Color                                         | White and selected RAL colors on request.                                                                     |
| % Solid Content by volume                     | 50 ± 2 depending on color                                                                                     |
| Diluent/Thinner                               | Breemo thinner ST 07                                                                                          |
| Drying Time at 25°C and relative humidity 50% | <ul style="list-style-type: none"> <li>• Touch Dry : 10 minutes</li> <li>• Dry to recoat : 2 hours</li> </ul> |
| Recommended DFT                               | 40 – 50 µm (multiple coats may be required)                                                                   |

### INSTRUCTIONS FOR USE

- Steel surface must be free from oil, grease, dirt, & other contaminants.
- Remove loose scale & rust by manual wire brush or suitable mechanical cleaning.
- Prime the surface with **BREEMO STEEL ZP FAST DRY**.
- Apply one or two coats of finish.
- Use in good ventilated areas and keep away from source of ignition as the product is flammable.

### APPLICATION TOOLS

Prefer spray application. Brush and Roller (only for difficult areas and for stripe coat)

### THEORETICAL COVERAGE

12.5 m<sup>2</sup> per lit at 40 microns DFT. Practical coverage varies depending on film thickness, surface porosity and losses.

### PACKAGING

Available in 20 litres, Special packs available on request.

### STORAGE & SHELF-LIFE

12 months in original tightly closed packs away from direct sunlight and excessive heat

Refer safety data sheet before using the product.

Contact SCIB representative for further clarifications.