

PRODUCT CODE 8007

TruCare Wood Primer

Asian Paints TruCare Wood Primer is a specially formulated product designed to protect and enhance the appearance of wooden surfaces. It provides a solid foundation for varnish, coatings and paint, ensuring durability and a lasting finish.

PRODUCT BENEFITS

- > Good coverage
- > Smooth Flow & Levelling
- > Strong Adhesion
- > Effective sealing of Wooden Surfaces .
- > Ensures Uniform and Durable finish.



SOLVENT BASED
 **asianpaints**

No Added Lead, Mercury,
 Arsenic & Chromium

Lead contents does not exceed 90 parts per million.

PRODUCT FEATURES


AVAILABLE PACKS



Shelf life: 36 months (3 years) in original tightly closed containers away from direct sunlight and excessive heat

COLOURS AVAILABLE

Pink/ White



Please note: Asian Paints TruCare Wood Primer is an undercoat

COVERAGE

On smooth flat mild Wood surface
 by brushing/Spraying




1 COAT

120 - 140
 sq.ft/ltr**

**Actual coverage may vary from the quoted coverage due to factors such as method and condition of application and surface roughness.

DRYING TIME TO RECOAT



AFTER 4-6 HOURS

FINISH



MATT

LOW SHEEN


HIGH SHEEN

HIGH GLOSS

✓ **SMOOTH**

Refer to sheen levels in technical details

RECOMMENDED USAGE



Asian Paints TruCare Wood Primer is suitable for priming wood substrates/Surfaces

HOW TO APPLY

APPLICATION PROCESS

PRODUCT	CODE	THINNER	DILUTION %	APPLICATION VISCOSITY ¹	RECOATING PERIOD
STEP 1 SANDING SURFACE PREPARATION	SAND THE SURFACE WITH EMERY PAPER 180 AND WIPE CLEAN.				
STEP 2 FIRST COAT TRUCARE WOOD PRIMER (BRUSH/SPRAY)	8007	 MTO*	5 - 10	SUITABLE FOR BRUSH/SPRAY APPLICATION	4 - 6 Hrs.
STEP 3 SANDING	SAND LIGHTLY WITH EMERY PAPER 180 AND WIPE CLEAN.				
STEP 4 TOP COAT APPLICATION AS PER RECOMMENDATION	APPLY TOP COAT AS REQUIRED.				

1. Recoat period is quoted for 25°C and 50% Relative Humidity; values may vary under different conditions.

2. MTO = Mineral Turpentine Oil.

ADDITIONAL INFORMATION

TECHNICAL DETAILS

- a. **Drying Time:**
Dry to recoat 4-6 Hrs
- b. **Flash Point IS101/1987 Part 1, Sec 6:**
>35°C (95°F)
- c. **Viscosity:**
100-120 Seconds by Ford Cup B4 at 30°C
- d. **Shelf Life:**
3-years from the MFD
- e. **Stability of thinned Paint:**
To be used within 24 hours

PRECAUTIONS

- This product is flammable.
- Do not apply when ambient temperature is less than 10°C or if the temperature might drop to this level within 4 hours of application.
- Work in a well-ventilated place. Wear protective clothing like overalls and gloves. Store the product at ambient conditions in well-ventilated locations and away from sources of ignition and fire. Do not over-thin or over-extend the brush.
- Avoid eye and skin contact. In case of eye and skin contact wash with plenty of clean water.
- Do not inhale or inject. In case of inhalation move to fresh air. Seek medical attention if symptoms persist.
- Use protective equipment like rubber/polythene gloves, safety goggles/glasses and face mask while handling the paint.
- In case of settling is noticed, homogenize the material by mixing and use.

SAFETY FEATURES

- Kindly refer to the MSDS for Asian Paints Wood Primer which gives detailed information on safety measures while handling the paint, available on request.
- Store the container with the lid tightly closed in an upright position, in a cool, dry place.
- Keep out of reach of children and away from eatables.
- May be harmful if swallowed. In case of ingestion, seek immediate medical attention.
- Wear eye protection during application. In case of contact with eyes, rinse immediately with plenty of water and seek medical advice.
- In case of skin contact, immediately wash skin with soap and plenty of water. Get medical attention if irritation develops or persists.
- Do not breathe vapour or spray. It is recommended to wear a suitable nose pad during sanding and surface preparation to avoid dust inhalation.
- Do not pour leftover paint down the drain or into water courses.
- In the event of spills, contain spillage using sand or earth.
- No added Lead, Mercury, Arsenic or Chromium compounds.
- Disposal in land filling and not in drain or any water channel.
- Lead content does not exceed 90ppm.



For enquiries, feedback and complaints,
please call toll-free number
16600124680/9802033515 or write to us at
weassure@asianpaints.com.np