DESCRIPTION

Causeway HV NC Sanding Sealer is a high viscosity, nitro cellulose based sealer specially formulated to provide a smooth surface for any kind of timber based furniture and fittings including doors & windows.

- High Viscosity
- High Build
- Good Filling
- Excellent Sanding Properties

TYPICAL USES

- HV Sanding Sealer is applicable for solid wood, MDF, rattan and veneered furniture& wall paneling.
- NC sanding sealer provides a quality sealer for timber wall paneling, office desks, chairs, cabinets and other items of quality furniture.

APPLICATION

- Apply over prepared surfaces
- Method of application
  - Conventional Spray
  - Brush

EQUIPMENT GUIDE

- Suction Guns
  1.8mm fluid tip at 350 kpa (50-55 psi) air pressure
- Pressure Pots
  1.5mm fluid tip with dedicated pot pressure air cap at 350 kpa air pressure and pot pressure of 45 kpa (6 psi)
- Airless
  9 – 13 thou fluid tip size and pump regulated to 400 kpa (50-60 psi). Viscosity dependent.
- Air Assisted Airless
  9 – 13 thou fluid tip size and pump regulated to 400 kpa (50-60 psi) with air assist regulated at 70 to 90 kpa (10-15 psi). Viscosity dependent.
- Curtain Coating
  Check suitability of equipment and ensure viscosity is maintained at 15-25 sec. with regular addition of NC Thinner to maintain operational viscosity.

HEALTH & SAFETY

Always keep paint out of reach of children. Ensure good ventilation during application and drying. Do not smoke while painting. Highly flammable. Store in a cool dry place away from heat and sparks.

CAUSEWAY PAINTS

TECHNICAL DATA SHEET
CAUSEWAY HV SANDING SEALER

TECHNICAL DATA

○ COLOR	: Colourless Transparent shades
○ COMPONENTS	: Single
○ FINISH	: Satin
○ CURING MECHANISM	: Air Dry
○ VISCOSITY	: 600 poise @ 30^0C
○ SPECIFIC GRAVITY	: ~ 1.000
○ VOLUME OF SOLIDS	: Approximately 45%
○ THINNER	: Causeway NC Thinner
○ MIXING RATIO	: 200 - 300% (Volume)
○ SPRAY VISCOSITY	: 25 sec (Ford 4)
○ RECOMMENDED THICKNESS PER COAT	: 25µm
○ THEORETICAL COVERAGE	: ~ 15m² / L (Based on 25µm DFT)
○ DRYING TIME	: 5 minutes (Touch dry) 30 minutes (Print free) 90 minutes (Sanding)
○ RE-COATING INTERVAL	: As per the requirement
○ POT LIFE	: N/A
○ SHELF LIFE	: 5 years (unopened)

PACKING

○ 5 Litres ○ 20 Litres

The Technical Data is provided only as general advice. However, since service and applications conditions are beyond our control, we do not accept liability relating to coverage, performance and injury arising from the use of our products based on these data. The above information may vary from time to time and we reserve the right to modify the data without prior notice.