DESCRIPTION

Causeway Max Cut is a two component polyester putty / metal filler, which is formulated for proper preparation of metal surfaces. It can be applied as a thick or thin layer. Specialties of this product are quick drying, easy to sand ability, excellent adhesion and flexibility.

- Polyester Based
- Excellent Adhesion
- Excellent Workability and Flexibility
- Excellent Sanadability
- Fast Drying

TYPICAL USES

- Used for filling and leveling of dented surfaces of automotive and machinery surfaces.

APPLICATION

- Apply over metal surfaces with the provided applicator
- Allow the putty to dry first before adding further layer of the putty for leveling.

APPLICATION INSTRUCTIONS

- Remove any dust, oil and other contaminants that may affect its adhesion property.
- Use Grade 40 abrasive paper to sand down the old surface if necessary.
- Ensure that all loose old paint flakes are removed before any application of the putty.
- Mix the two components (100:2) thoroughly before applying.
- Apply the putty before the pot-life is due.
- Perform sanding only after the putty is fully dried.
- Wash primer or etch primer should be applied on top of poly putty.

HEALTH & SAFETY

Always keep out of reach of children. Ensure good ventilation during application and drying. Do not smoke while applying. Highly flammable. Store in a cool dry place away from heat and sparks. Do not add the hardener mixed base to the tin. Hardener is toxic, if swallowed seek medical advice immediately.

TECHNICAL DATA SHEET

CAUSEWAY MAX CUT WITH HARDENER

TECHNICAL DATA

○ COLOR	: Off White
○ COMPONENTS	: Two
○ FINISH	: Matt
○ CURING MECHANISM	: Reaction between two Components
○ VISCOSITY	: 800 Poise
○ SPECIFIC GRAVITY	: ~ 1.1
○ MIXING RATIO	: 100g : 2g (Base : Hardener)
○ RECOMMENDED THICKNESS PER COAT	: approx 3mm
○ DRYING TIME	: 10 – 15 Miniutes
○ POT LIFE	: approx 3 - 5 minutes
○ RECOMMENDED SANDING TIME	After 10 -15 Minutes
○ SHELF LIFE	: Best before 12 months

PACKING

- 4 Kg of Base+ 80 g of Hardener
- 1.5 Kg of Base+ 30 g of Hardener
- 300 ml of Base + 7 g of Hardener
- 500 ml + 15 g of Hardener

Causeway Paints Lanka (Pvt) Ltd.
#15, Noel Mendis Mawatha, Modarawila Industrial Estate, Panadura, Sri Lanka.
M: 038-2240040
W: www.causewaypaints.com

Issue Date: 04/01/2026 **Rev: 01**

The Technical Data is provided only as general advice. However, since service and applications conditions are beyond our control, we do not accept liability relating to coverage, performance and injury arising from the use of our products based on these data. The above information may vary from time to time and we reserve the right to modify the data without prior notice.