DESCRIPTION

Sunny 2K auto refinish (4:1) is a two-component polyurethane acrylic paint for refinishing coat with UV Protection.

- Two component polyurethane automotive coating.
- Good gloss retention
- Good weather resistance
- Provides unique hardness, impact resistance, flexibility and elasticity.
- Possess excellent water, gasoline and chemical resistance.

TYPICAL USES

- Used as automotive coating for its good physical and weathering properties.
- Also, can be used for industrial applications.

APPLICATION

- Method of application
  - Spray

APPLICATION INSTRUCTIONS

- Ensure that the surface is free of all dirt, oil, grease, rust and any other materials on the surface that may adversely affect its adhesion properties.
- Ensure that the base coat is also properly applied before application of the Clear coat.
- Mix the Sunny 2K solid paint and Sunny 2k Hardener together thoroughly. Adjust the viscosity of the mixture with thinner to the required viscosity before application.

HEALTH & SAFETY

Always keep paint out of reach of children. Ensure good ventilation during application and drying. Do not smoke while painting. Highly flammable. Store in a cool dry place away from heat and sparks.

C.P.T. CAUSEWAY PAINTS

TECHNICAL DATA SHEET

SUNNY 2K SOLID (4:1)

TECHNICAL DATA

○ COLOR	: As per request
○ COMPONENTS	: Two
○ FINISH	: High - Gloss
○ CURING MECHANISM	: Chemical reaction Between components
○ VISCOSITY	: 28 sec (Ford 4)
○ SPECIFIC GRAVITY	: ~1.000
○ VOLUME OF SOLIDS	: ~ 55 - 60%
○ THINNER	: Causeway Uni Thinner 171 (20% - 25%)
○ MIXING RATIO	: Base: Hardener = 4:1
○ SPRAY VISCOSITY	: 18- 20 seconds
○ RECOMMENDED THICKNESS PER COAT	: 25 - 35µm (DFT)
○ THEORETICAL COVERAGE	: 10-12 m^2 / L (25µm DFT)
○ DRYING TIME	: Touch Dry : 120 minutes Polishing : 1 Week
○ POT LIFE	: 150Minutes @ 30^0C
○ SHELF LIFE	: Best before 36 months

PACKING

- 1 Litre

The Technical Data is provided only as general advice. However, since service and applications conditions are beyond our control, we do not accept liability relating to coverage, performance and injury arising from the use of our products based on these data. The above information may vary from time to time and we reserve the right to modify the data without prior notice.