DESCRIPTION

Causeway Etch Primer is a dual package system containing Etch Primer Base and Etch Primer Activator. It is specially formulated to enhance adhesion on non ferrous metal surfaces (galvanized, aluminium, zinc etc.), Also can be applied on ferrous metal surfaces. It will help to adhere the paint strongly to the substrate and act as protective substrate for further painting.

- Anti-Corrosive property.
- Excellent Adhesion onto Aluminum, Zinc and other light metals.
- Rapid Drying

TYPICAL USES

- Act as a pre-treatment primer for aluminum and galvanized surfaces.
- Good primer for marine and structural steel works.

APPLICATION

- Apply over fresh, cleaned surfaces.
- Method of application
  - Conventional Spray
  - Brush

APPLICATION INSTRUCTIONS

- Ensure that the surface is free of oil, grease, dust and any other contaminants that may affect its adhesive property.
- Spray a coat of Etch Primer.
- Allow the paint to dry about 1 hour before applying the top-coat.
- The topcoat should be applied within 24 hours.

HEALTH & SAFETY

Always keep paint out of reach of children. Ensure good ventilation during application and drying. Do not smoke while painting. Highly flammable. Store in a cool dry place away from heat and sparks.

CAUSEWAY PAINTS

TECHNICAL DATA SHEET
CAUSEWAY ETCH PRIMER BASE

TECHNICAL DATA

○ COLOR	: Transparent Yellow
○ COMPONENTS	: Dual
○ FINISH	: Low - Sheen
○ CURING MECHANISM	: Acid catalyses
○ VISCOSITY	: ~60 sec Ford cup 4
○ SPECIFIC GRAVITY	: ~ 0.94 +/- 0.05
○ VOLUME OF SOLIDS	: Approximately 25%
○ THINNER	: Not required
○ MIXING RATIO	: Base : Hardener = 1:1
○ SPRAY VISCOSITY	: 15 sec (Ford 4)
○ RECOMMENDED THICKNESS PER COAT	: 10 - 15µm
○ THEORETICAL COVERAGE	: ~ 10m²/L (Based on 15µm DFT)
○ DRYING TIME	: 5 minutes (Touch dry) 1 hours (Hard dry)
○ RE-COATING INTERVAL	: 1 hours
○ POT LIFE	: 8 hours
○ SHELF LIFE	: Best before 24 months

PACKING

○ 1 Litre ○ 4 Litres

The Technical Data is provided only as general advice. However, since service and applications conditions are beyond our control, we do not accept liability relating to coverage, performance and injury arising from the use of our products based on these data. The above information may vary from time to time and we reserve the right to modify the data without prior notice.