DESCRIPTION

Causeway Sunny Underbody Seal (Black) is a solvent base underbody coating based on bitumen/rubber. Offers lasting and flexible protection from stone chipping and corrosion. After complete drying, the coating exhibits an abrasion-resistance and is also an excellent vibration control material.

- Long Term Protection
- Anti- Drone Effect
- High Solid Content
- Excellent Adhesion
- Permanently Elastic
- Temperature Resistant

TYPICAL USES

SUNNY UNDERBODY BLACK is used as an under body coating on passenger cars for areas which are mechanically heavily used. And it is particularly suitable for motor vehicle bodies, wheel casings, front spoilers, car doors, edges, joints, bonnets, rear ends, deck lids, etc.

APPLICATION

The product can be applied by brush/spray or spatula. Application by Underseal spray gun is highly recommended. Due to its excellent sag resistance, the material can be applied up to a high layer thickness.

SURFACE PREPERATION

Surface to be painted with **SUNNY UNDERBODY BLACK** have to be cleaned well and rust must be removed. The area must be dry and free of oil, grease, dirt and to great extent free of dust.

APPLICATION INSTRUCTIONS

- Use outdoors or in a well-ventilated area such as an open garage. Mix the contents thoroughly before use. Do not dilute with thinner, apply as it is.
- **SUNNY UNDERBODY BLACK** can be applied by brush or spatula in one step up to 4mm layer thickness. After dying over night the vehicle is ready for use again. For full curing 24-36 hours are necessary.

HEALTH & SAFETY

Always keep paint out of reach of children. Ensure good ventilation during application and drying. Do not smoke while painting. Highly flammable. Store in a cool dry place away from heat and sparks.

CAUSEWAY PAINTS

TECHNICAL DATA SHEET
SUNNY UNDER BODY BLACK

TECHNICAL DATA

○ COLOR	: Black
○ COMPONENTS	: Single
○ FINISH	: Semi-gloss
○ CURING MECHANISM	: Air dry
○ VISCOSITY	: 30 seconds (Ford 4 cup)
○ SPECIFIC GRAVITY	: 1.294
○ VOLUME OF SOLIDS	: 60%
○ THINNER	: Not required
○ MIXING RATIO	: Not required
○ SPRAY VISCOSITY	: N/A
○ RECOMMENDED THICKNESS PER COAT	: As per the requirement
○ THEORETICAL COVERAGE	: Depends on the DFT
○ DRYING TIME	: Touch Dry : 2 Hours Hard Dry : 16 Hours
○ RE-COATING INTERVAL	: 24 Hours
○ SHELF LIFE	: Best before 24 months

PACKING

○ 1 Litre ○ 4 Litres

Issue Date: 24/10/2016 **Rev: 01**

The Technical Data is provided only as general advice. However, since service and applications conditions are beyond our control, we do not accept liability relating to coverage, performance and injury arising from the use of our products based on these data. The above information may vary from time to time and we reserve the right to modify the data without prior notice.