

PRODUCT CODE 1087

TruCare Yellow Metal Primer

Asian Paints TruCare Yellow Metal Primer provides excellent rust protection to metal surfaces keeping them corrosion free and beautiful for longer time.

PRODUCT BENEFITS

Protection

High protection against rust - 20 times stronger than ordinary metal primer. This product to be top coated with products like Apcolite Premium Gloss Enamel or Apcolite Premium Satin Enamel.

Performance

Zinc Phosphate based. Doesn't contain hazardous material of chrome. Excellent adhesion of paint film to the metal surface



SOLVENT BASED


asianpaints

LEAD FREE* GUARANTEE

* All Asian Paints products contain no added Lead, Mercury, Arsenic or Chromium from April 2008.

PRODUCT FEATURES

AVAILABLE PACKS



Shelf life: 2 years from date of manufacture in original tightly closed containers away from direct sunlight and excessive heat.

COVERAGE



*Always apply two coats of this primer for the desired performance.

HOW TO APPLY

PAINT APPLICATION PROCESS

APPLICATION	CODE	THINNER	DILUTION %	APPLICATION VISCOSITY*	RECOATING PERIOD
STEP 1 RUST REMOVAL	REMOVE EXISTING RUST IF ANY BY CHIPPING OR SCRAPING.				
STEP 2 SANDING	SAND THE SURFACE WITH EMERY PAPER 180 AND WIPE CLEAN				
STEP 3 TRUCARE YELLOW METAL PRIMER	1087	MTO**	BRUSH 6 - 8 SPRAY 8 - 10	BRUSH 55 - 60 SPRAY 20 - 25	8 HRS
STEP 4 SANDING	SAND THE SURFACE WITH EMERY PAPER 320 OR 400 AND				
STEP 5 TRUCARE KNIFING PASTE FILLER	0016	MTO	BASED ON REQUIREMENT	BASED ON REQUIREMENT	6 - 8 HRS
STEP 6 SANDING	SAND THE SURFACE WITH EMERY PAPER 180 AND WIPE CLEAN				
STEP 7 TRUCARE YELLOW METAL PRIMER	1087	MTO	BRUSH 6 - 8 SPRAY 8 - 10	BRUSH 55 - 60 SPRAY 20 - 25	8 HRS

* As measured in a Ford cup B4. ** Mineral Turpentine oil. Re-coat times are quoted for 25°C and 50% Relative Humidity, these may vary under different conditions.

ADDITIONAL INFORMATION

POST PAINTING CARE

For the best performance of the paint, ensure proper cleaning of all dust, oil and external particles, if any, at regular intervals of six months.

TECHNICAL DETAILS

a. Sheen levels: N/A

b. Flash point IS101/1987 Part 1 Sec 6:

Less than 35 Deg C (95 Deg F)

c. Stability of paint: To be used within 24 hours

PRECAUTIONS

- › Do not apply when ambient temperature is less than 10°C or if the temperature might drop to this level within 4 hours of application
- › Do not over-thin or over-extend the brush.
- › Stir well and strain before use.

SAFETY FEATURES

- › Kindly refer to the MSDS for TruCare Yellow Metal Primer which gives detailed information on safety measures while handling the paint.
- › Store the product at ambient conditions in well ventilated locations and away from the source of ignition and fire.
- › Do not apply when ambient temperature is less than 10°C or if the temperature might drop to this level within 4 hours of this application.
- › Avoid eye and skin contact. In case of eye and skin contact, wash with plenty of clean water.
- › Do not inhale or ingest. In case of inhalation move to fresh air and seek medical attention if the systems persists in both the cases.
- › Use protective equipment like rubber / polyethylene gloves, safety goggles / glasses, face mask while handling the paint.
- › Stir well and strain before use.