

EPIMASTIC 6100 MBS

High Build Epoxy Mastic

PRODUCT DESCRIPTION

A high build surface tolerant epoxy primer cum finish coat containing anticorrosive pigments & colorants which provides excellent protection for steel. Recommended to use only for interior and not for exterior exposed conditions.

DESIGNED USE

- High resistance to impact and abrasion.
- Good adhesion over new and aged epoxy & alkyd coatings.
- As a chemically resistant finish for structural steel, process equipment, pipe work etc.
- As a general maintenance coating for onshore and offshore installations.
- Suitable as primer cum finish for upto C5 Environment as per ISO12944 Part 2 along with suitable topcoats

PHYSICAL DATA

| | |
|---|---|
| VOLUME SOLIDS (Based on ASTM D2697) | 70 % ± 2 % |
| TYPICAL DRY FILM THICKNESS | 150 microns |
| WET FILM THICKNESS | 215 microns |
| THEORETICAL COVERAGE | 4.7 m ² /litre @ 150 microns DFT |
| VOC "As Supplied" (Based on ASTM D3960) | 262 gms/ltr |
| COLOUR | Limited Colors |
| FINISH | Slight Sheen |

APPLICATION DETAILS

| | |
|-------------------------------|---|
| METHOD OF APPLICATION: | This is the recommended method of application: Maximum 5% Thinner may be added. |
| AIRLESS SPRAY | Tip Size: 0.48 - 0.58 mm (0.019 - 0.023 in) Pressure: 110 - 160 kg/cm ² (1600 - 2300 psi) |
| CONVENTIONAL SPRAY | This is also a suitable method of application. Maximum 20% Thinner may be added Tip Size: 1.80 - 2.20 mm (0.071 - 0.087 in) Pressure: 2.75 - 3.45 kg/cm ² (40 - 50 psi) |
| BRUSH OR ROLLER | May be used for difficult shapes or touch-up. However, additional coats may be required to achieve the recommended film thickness. |

DRYING TIME:

| Surface Temperature | Touch Dry | Hard Dry | Over coating Interval | | Pot Life |
|---------------------|-----------|----------|-----------------------|------------|----------|
| | | | Minimum | Maximum | |
| 15°C | 3 Hrs | 6 Hrs | 6 Hrs | Indefinite | 2 Hrs |
| 25°C | 1½ Hrs | 3 Hrs | 3 Hrs | Indefinite | 1 Hr |
| 35°C | 1 Hr | 2 Hrs | 2 Hrs | Indefinite | 30 mins |
| 45°C | 10 mins | 20 mins | 20 mins | Indefinite | < 30 min |

| | |
|--------------------------|---|
| NO. OF COMPONENTS | Two |
| Mixing Ratio | 2 part Base to 1 part Hardener (by volume) |
| Application Conditions | Do not apply this product if the Relative Humidity exceeds 85% or if the substrate temperature is within 3°C of the dew point |

ADDITIONAL INFORMATION

| | |
|----------------------------|---|
| Thinner / Cleaning solvent | Solvalux 7-45 |
| Storage Instruction | Store in a cool shaded dry area |
| Flash Point | Mixed 30°C |
| Packaging | 20 liters |
| Shelf Life | 12 months from the date of manufacture. |

EPIMASTIC 6100 MBS**High Build Epoxy Mastic****SURFACE PREPARATION**

- The life-span and performance of this coating is directly related to the degree of surface preparation.
- Remove all wax, oil and grease by solvent cleaning in accordance with the guide lines given by SSPC-SPI.
- Where necessary remove weld spatter and round off all rough weld seams and sharp edges to a smooth surface.
- Soluble salts, dirt and dust must be removed prior to coating. Dry brushing should be sufficient. A freshwater wash must follow to remove all soluble salts.
- Remove scale by chipping, needle gun or spot blasting. Any loose or flaking coatings should be taken back to a firm edge.
- Abrasive blast clean to a minimum standard of Sa 2 Swedish standard SIS 05 59 00 or ISO 8501 - 1 : 1988.
- After blasting, remove dust from the surface.
- The surface to be coated must be clean and dry.

TYPICAL COATING SYSTEMS

| System | Priming | 2 nd Coat | 3 rd Coat (Optional) |
|------------------------|-------------------------|----------------------|---------------------------------|
| Single Coat | Epimastic 6100 MBS | | |
| Two Coats | Epimastic 5500 M | Epimastic 6100 MBS | |
| Epoxy Zinc Rich System | Zincanode 600/ 620/ 690 | Epimastic 6100 MBS | |
| Epoxy Zinc Rich System | Zincanode 600/ 620/ 690 | Epimastic 5500 M | Epimastic 6100 MBS |

PRODUCT USE RESTRICTIONS

- This Product is not suitable for use in immersed conditions without a topcoat.
- Generally recommended for interior use.
- Dry heat resistance up to 100°C.
- Application method and higher drying temperature may affect the colour of the coating.
- As common with all Epoxy products, this product also will tend to discolour and chalk on exposure to direct sunlight.
- May also be applied between 100 and 200 Microns DFT.
- Contact Berger Representative for suggesting suitable paint system.

SAFETY PRECAUTIONS

- Avoid contact with the skin and eyes. Wear suitable protective clothing such as overalls, goggles, dust masks and gloves. Use a barrier cream.
- Ensure that there is adequate ventilation in the area where the product is being applied. Do not breathe vapor or spray.
- This product is flammable. Keep away from sources of ignition. Do not smoke. Take precautionary measures against static discharge. In case of fire – blanket flames with foam, carbon dioxide or dry chemicals
- Refer to MSDS for further information.

FIRST AID

- Eyes: In the event of accidental splashes, flush eyes with water immediately and obtain medical advice
- Skin: Wash skin thoroughly with soap and water or approved industrial cleaner.
- DO NOT USE solvent or thinners.
- Inhalation: Remove to fresh air, loosen collar and keep patient rested.
- Ingestion: In case of accidental ingestion, DO NOT INDUCE VOMITING. Obtain immediate medical attention

DISCLAIMER

The information provided on this data sheet is not intended to be complete and is provided as general advice only. It is the responsibility of the user to ensure that the product is suitable for the purpose for which he wishes to use it. As we have no control over the treatment of the product, the standard of surface preparation of the substrate, or other factors affecting the use of this product, we are not responsible for its performance nor would we accept any liability whatsoever or howsoever arising from the use of this product unless specifically agreed to in writing by us. The information contained in this data sheet may be modified by us from time to time, and without notice, in the light of our experience and continuous product development.