

Kadisco Super Synthetic Enamel

Product Description

An enamel based on suitably modified alkyd containing titanium dioxide and other colorfast pigments to provide a tough, durable and hardwearing high gloss finish with good flow, hiding power and film build-up.

Recommended Areas of Application

Area of Use: Interior & Exterior

Substrate: Metal, Timber & Masonry surfaces

Technical Data

Sheen Variants: High Gloss & Matt

Volume Solids: 44% $\pm$ 2%

Theoretical Covering Capacity		
Recommended Dry Film Thickness per coat		Theoretical Spread rate
Minimum	30 microns	14.66 m ² / ltr.
Maximum	50 microns	8.80 m ² / ltr.
Typical	40 microns	11.00 m ² / ltr.

Practical Covering Capacity
For estimation of practical covering capacity, following factors to be taken into account: surface profile, uneven application, over spray, losses in container and equipment etc.

Drying time	Substrate Temp.	Touch Dry	Overcoating Interval	
			Minimum	Maximum
	25°C	1½ hours	24 hours	Indefinite
	35°C	1 hour	18 hours	Indefinite
	45°C	45 minutes	12 hours	Indefinite

Application Data

Method of application: Roller/Brush application

Thinner:

Thinning ratio (by vol.): Use 5% to 10% for ease of application depending on the method of application.

Surface Preparation

The performance of this coating is directly related to the degree of surface preparation.

- Ensure surface is clean, dry and free from all contaminants.
- Steel: Remove rust, if any, by sand blasting or other methods to Swedish Standard Sa 2½.
- Timber: Wood may be treated further with Berger Wood Preservative.
- Masonry: Surface must be sound and free from laitance. Remove laitance by wire brush or sweep last.

Kadisco Super Synthetic Enamel

Application Details

- Ensure adequate ventilation during application and drying.
- Do not apply when humidity exceeds 85% and condensation is likely.
- Surface temperature should be 3°C or more above dew point.
- Stir the contents thoroughly before and during use, with a broad flat stirrer, using an upward lifting action.

Note: Use of Alkyd systems on masonry necessitates extra precautions such as, adequate ventilation and light during and for a length of time after application.

- **Airless Spray:** Tip Size: 0.22 – 0.30 mm (0.009 – 0.011 in)
Tip Pressure: 90 – 130 kg / cm² (1300 – 1800 psi)
- **Conventional Spray:** Use normal spray equipment
- **Brush or Roller:** Apply an even coat taking care to avoid rungs and sags. More than one coat will be required.

TYPICAL PAINT SYSTEM		
Masonry	Steel	Timber
1 coat Kadisco Wall Primer	1 coat Metal Primer	1 coat Wood Primer
2 coats Kadisco Wall Plaster	2 coats Kadisco Super Synthetic Enamel	2 coats Kadisco Wall Plaster
2 coats Kadisco Super Synthetic Enamel		2 coats Kadisco Super Synthetic Enamel
For alternate system suggestion please contact Sales Representative		

Storage, Safety Information and Precautions

- Keep out of reach of children.
- Store in cool, dry conditions; ensure adequate ventilation during application.
- Avoid contact with skin and eyes; wear suitable protective clothing such as overalls, goggles, dust masks and gloves.
- Flash Point: 40° C
- Shelf life up to 12 months from the date of manufacture.

First-Aid

- **Eyes:** In the event of accidental splashes, flush eyes immediately with warm water and obtain medical advice.
- **Skin:** Wash skin thoroughly with soap and water, or with an approved industrial cleaner.
- **Inhalation:** Move patient to fresh air, loosen collar and keep patient rested.
- **Ingestion:** Do not induce vomiting. Obtain immediate medical attention.
- Dispose in landfill only.

Kadisco Super Synthetic Enamel

Disclaimer

The information provided in this data sheet is not intended to be complete. It is the responsibility of the user to ensure that the product used is suitable for the purpose it is meant to serve. In view of various factors affecting the performance of the coating, we cannot assume responsibility for the product performance, nor do we accept any liability arising from use of this product, unless specifically agreed to in writing by us. The information provided in the data sheet may be modified by us without notice.